

Metal foil clad laminate for PCB(s) - has base of nonwoven glass fabric impregnated with resin contg. inorganic filler

Patent Assignee: SHIN KOBE ELECTRIC MACHINERY (KOBE)

Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
JP 5261855	A	19931012	JP 9262687	A	19920319	199345 B

Priority Applications (No Type Date): JP 9262687 A 19920319

Patent Details:

Patent No	Kind	LaN Pg	Main IPC	Filing Notes
JP 5261855	A	3	B32B-015/08	

Abstract (Basic): JP 5261855 A

A part or whole of a base material is glass nonwoven fabric which is impregnated with resin contg. 60-80 wt. parts or less of inorganic filler with average dia. of 10 micron or less (pref. 5 micron or less) per 100 wt. parts of the resin.

USE/ADVANTAGE - For printed circuit boards. Smaller rate of expansion in thickness direction of the laminate.

In an example, a varnish, methylethylketone-methylglycol solution (resin solid content = 60 wt.%) of 100 wt. parts of Epicoat 1001 (YUKA SHELL KK), 4 wt. parts of dicyandiamide and 0.5 wt. parts of 2-ethyl-4-methylimidazole is prepared. 0.18 micron thick glass fabric is impregnated with the varnish and dried to skin prepreg. with 45 wt.% resin content. 80 wt. parts of talc with 5 micron dia. (NIPPON TALC KK) is added in the varnish to 100 wt. parts of resin solid. Glass nonwoven fabric (basis weight = 75 g/m²) is impregnated with the filler contg. varnish and dried to core prepreg. (resin content = 85 wt.%). Three sheets of core prepreg. skin prepreg. on each side and 18 microns thick copper foil on each outer surface are piled up and moulded at 170 deg. C, 60 kg/cm² for 90 min. to give 1.6 mm thick double copperclad laminate.

Dwg.0/0

Title Terms: METAL; FOIL; CLAD; LAMINATE; PCB; BASE; NONWOVEN; GLASS; FABRIC; IMPREGNATE; RESIN; CONTAIN; INORGANIC; FILL

Index Terms/Additional Words: PRINTED; CIRCUIT; BOARD

Derwent Class: A85; L03; P73; V04

International Patent Class (Main): B32B-015/08

International Patent Class (Additional): B32B-017/04; B32B-027/20; H05K-001/03

File Segment: CPI; EPI; EngPI

?